

Appl. No. 09/889,496  
 Amendment Dated October 27, 2003  
 Reply to Final Office Action of July 25, 2003


### AMENDMENTS TO THE CLAIMS

1. **(Currently Amended)** ~~Water borne~~ A water-borne paint composition which comprises a binder and a coalescent agent alone or together with at least one member of the group consisting of surfactants, dispersion agents, thickening agents, conservation agents/fungicides, antifoaming agents and fillers~~binder, a coalescent agent and optionally admixtures and auxiliary agents known per se, and pigments, calcium carbonate, titanium dioxide, pH regulating agents and aqueous ammonia,~~ characterized in that at least 20 % of the film forming agent is formed by a glycidyl ether of formula I



wherein R is a linear or branched, saturated or unsaturated C<sub>3</sub>-C<sub>20</sub> hydrocarbon and X is hydrogen or a hydroxyl group,

or a glycidyl ester of formula II



wherein R' is a linear or branched, saturated or unsaturated ~~C<sub>3</sub>-C<sub>20</sub>~~ C<sub>2</sub>-C<sub>20</sub> hydrocarbon and X' is a methyl group, a methylene hydroxy group or a carboxyl or lower carboxylate group,

or a mixture thereof.

Appl. No. 09/889,496  
Amendment Dated October 27, 2003  
Reply to Final Office Action of July 25, 2003

2. **(Previously Amended)** The paint composition according to claim 1, characterized in that it contains 0.01 to 20 wt.-% glycidyl ether or ester or admixture thereof based on the dry matter content of the composition.
3. **(Previously Amended)** The paint composition according to claim 1 or claim 2, characterized in that it contains 3 to 80 wt.-% of a binder which can be dispersed in water.
4. **(Original)** The paint composition according to claim 3, characterized in that the binder is poly(vinyl acetate), polyacrylate, poly(vinyl alcohol), starch, carboxymethylcellulose, hydroxyethyl cellulose or alkyd.
5. **(Original)** The paint composition according to claim 4, characterized in that the binder forms a hard polymer film when the composition has dried.
6. **(Canceled)**
7. **(Previously Amended)** The paint composition according to claim 1, characterized in that the hydrocarbon residue of the glycidyl ether is derived from 1-butanol, 2-butanol, isobutanol, 1-pentanol, isopentanol, 1-hexanol, 2-ethylhexanol, 1-heptanol, 1-octanol, 2-ethyl-1,3-hexanediol, neopentyl glycol, 2-butyl-2-ethyl-1,3-propanediol, trimethylol ethane, trimethylol propane, 1,4-butanediol, neodecane alcohol, 1-6-hexanediol, 1,10-decanediol or 2-ethyl-2-hexen-1-ol.
8. **(Canceled)**
9. **(Previously Amended)** The paint composition according to claim 1,

Appl. No. 09/889,496  
Amendment Dated October 27, 2003  
Reply to Final Office Action of July 25, 2003

characterized in that the carboxylic acid residue of the glycidyl ester is derived from butanoic acid, isobutanoic acid, pentanoic acid, isopentanoic acid, 1-hexanoic acid, 2-ethylhexanoic acid, heptanoic acid, octanoic acid, neodecanoic acid, 2-hydroxy-isobutanoic acid, 2,2-dimethyl-3-hydroxypropanoic acid, 2-ethyl-2-hexenoic acid, oleic acid, linolic acid, adipic acid, fumaric acid, maleic acid, succinic acid, glutaric acid or an anhydride or another derivative thereof.

10. **(Previously Amended)** The paint composition according to claim 1, characterized in that the coalescent agent is 2-ethylhexylglycidyl ether, octyl glycidyl ether, mono- or diether of neopentylglycol or triglycidyl ether of trimetanolpropane, or 2-ethylhexyl glycidyl ester, octyl glycidyl ester or isopentyl glycidyl ester or methyl glycidyl ester of glutaric acid.

11. **(Previously Amended)** The paint composition according to claim 1, characterized in that its pH is below about 8.5.

12. **(Previously Amended)** The paint composition according to claim 1, characterized in that it contains in addition to the glycidyl ether or ester or admixture thereof, at least one other coalescent agent, the proportion of the glycidyl ether or ester or admixture thereof of the coalescent agents of the composition amounting to at least 20 wt.-%.

13. **(Previously Amended)** The paint composition according claim 12, characterized in that the other film forming agent is the phenyl ether of ethyleneglycol, 2,2,4-trimethyl-1,3-pentanediol monoisobutyrate or n-butyl ether acetate of diethyleneglycol.

Appl. No. 09/889,496  
Amendment Dated October 27, 2003  
Reply to Final Office Action of July 25, 2003

14. **(Currently Amended)** ~~Method A~~ method of accelerating the hardening of an aqueous paint composition containing ~~binder, binder and coalescent agent alone~~ or together with at least one member of the group consisting of surfactants, dispersion agents, thickening agents, and optionally admixtures and auxiliary agents known per se, characterized by conservation agents/fungicides, antifoaming agents and fillers and pigments, calcium carbonate, titanium dioxide, pH regulating agents and aqueous ammonia, characterized by incorporating into the composition a mono-glycidyl ether or ester or a mixture thereof, wherein the hydrocarbyl residue of the alcohol or carboxylic acid, respectively, of the ether or ester comprises a linear or branched, unsaturated or saturated hydrocarbon having 3 to 20 carbon atoms, the proportion of the glycidyl ether and/or ester or admixture thereof being at least 20 wt.-% of the film forming agents of the paint composition.

15. **(Previously Amended)** The method according to claim 14, characterized by incorporating at least 50 wt.-% of a glycidyl ether or ester or admixture thereof, whereby the paint composition attains at least 70% of its final hardness within a day.

16. **(Currently Amended)** A method for forming films in aqueous paint compositions comprising admixing a mono-glycidyl ether or ester or a mixture thereof with a latex dispersion, wherein said ether or ester contains a linear or branched, saturated or unsaturated hydrocarbyl residue comprising 3 to 20 hydrocarbyl residues with 3 to 20 carbon atoms which are linked to the glycidyl group via an ether or ester bond.

17. **(Previously Presented)** The paint composition according to claim 3, wherein said binder is 4 to 60 wt.-%.

Appl. No. 09/889,496  
Amendment Dated October 27, 2003  
Reply to Final Office Action of July 25, 2003

18. **(Previously Presented)** The paint composition according to claim 1, wherein said C<sub>2</sub>-C<sub>20</sub> hydrocarbon of said formula II contains one or several hydroxyl groups.

19. **(Previously Presented)** The paint composition according to claim 11, wherein said pH is below about 8.0.

20. **(Previously Presented)** The paint composition according to claim 1, wherein said C<sub>3</sub>-C<sub>20</sub> hydrocarbon of said formula I contains one or several hydroxyl groups.

21. **(Previously Presented)** The paint composition according to claim 12, wherein said coalescent agents amount to at least 50 wt.-%.